

Parameters of nitrile rubber sheets

By [Nitrile Rubber Sheets](#) - www.dongrubber.com, sales@dongrubber.com, Date: Sep.01.06

Nitrile Rubber Sheet used where temperature resistance, oil resistance, flame resistance is required. There are more than 320 species of [nitrile rubber sheets](#), following are the parameters of some common nitrile rubbers:

Name& level	Origin	Model	Mooney viscosity	Combined acrylonitrile content%	specific gravity
Low-medium acrylonitrile content (26-30%)	JSR	N240S	56	26	0.96
	Ruiwen	N41	78	29	0.97
	Korea LG	B7150	54	29	0.97
Medium-high acrylonitrile content (31-35%)	JSR	N230S	56	35	0.98
	Korea LG	B6240	41	34	0.98
	Korea LG	B6280	76.5	33.4	0.98
	Korea LG	B6250	50	33.4	0.98
High acrylonitrile content (36-45%)	JSR	N220S	56	41	1
	Korea LG	B3250	50	42	0.99
	Korea LG	B3280	80	42	0.99